

## Zhejiang Shuntai Rubber And Plastic Technology CO., LTD.

## Foaming agent (AC) testing report

**Executive standard:** <u>Internal standard</u>

Sampling location: AC workshop Batch number: 2019072501

Sampling time: <u>07/26/2019</u> Analysis date: <u>07/26/2019</u>

Style: SJ160 Quantity: 5000KGS

Item	Required indicator	Analysis result	Conclusion
Exterior	Light yellow powder	Light yellow powder	Pass
Starting temperature °C≥	150-160	158	Pass
End temperature °C≥	180-190	186	Pass
Gas production (average) ML/g ≥	160-170	164	Pass
Average particle size D50um≤	6-8	6.8	Pass
Reduced weight after heating≤	0.1-0.15	0.12	Pass
ΡΗ ≽	7.5-8.5	8	Pass

Auditor: Hu Caizhen Laboratory technician: Zhang