



Zhejiang Shuntai Rubber And Plastic Technology CO., LTD.

Foaming agent (TSH) testing report

Executive standard: Internal standard

Sampling location: White foamingagent workshop Batch number: 2019071401

Sampling time: 07/15/2019 Analysis date: 07/15/2019

Style: TSH Quantity: 500KGS

Item	Required indicator	Analysis result	Conclusion
Exterior	White powder	White powder	Pass
Decomposition temperature $^{\circ}\text{C} \geq$	143-147	145	Pass
Gas production (average) ML/g \geq	120-130	125	Pass
Average particle size D50um \leq	10-15	6.58	Pass
Moisture% \leq	0.5	0.23	Pass
Content% \geq	96-98	98.2	Pass
Ash %	0.1	0.05	Pass
PH \geq	5.0-7.5	6.6	Pass

Auditor: Hu Caizhen

Laboratory technician: Zhang Yi

